

TEGO® RC 1401

Product description

TEGO® RC 1401 is an UV curable solvent-free epoxy silicone release coating for paper and film. TEGO® RC 1401 is used to provide very easy release values.

Physical properties

Active matter	100 %
Volatile content	< 1 %
Viscosity, 25 °C (77 °F)	~ 350 mPa*s
Specific gravity, 25 °C (77 °F)	~ 1 g/cm ³
Colour	yellowish
Appearance	clear
Flash point (DIN 51758)	> 100 °C (> 212 °F)

The cationic curing mechanism of TEGO® RC 1401 does not require nitrogen inerting and can be cured under atmospheric conditions.

Cationic curing systems are catalyzed. The catalyst may be poisoned by alkalines, sulphur, phosphorous, amine and other components. The cure speed and release properties are therefore dependent on the curing conditions, the choice of substrate and the adhesive system.

Very low or very high humidity may also have an influence on the possible cure speed and the release properties.

Application fields

The cationic curing TEGO® RC 1400 series was developed to complement the radical UV/EB curable TEGO® RC silicone acrylates (RC 700/900 series). In some applications, the requirements for the release coating and the non-availability of inerted UV curing units may suggest the use of cationic curing silicones.

Advantages

- Easy to handle and use
- Inerting not required
- Low temperature impact to substrates
- Low extractables
- Stable release from most PSA's
- Low release values
- Sensitized for faster cure speed

Dosage/Handling

With the addition of 1 to 3% of the cationic photo catalyst TEGO® PC 1467, TEGO® RC 1401 is ready for UV curing.

This blend has a good adhesion on all substrates. The adhesion to the substrate can be improved by corona pre-treatment.

TEGO® RC 1401 contains the sensitizer ITX, enabling improved cure speed and reliability.

Controlled increase of the release value is possible by adding TEGO® RC 1412. The necessary addition level depends on the individual application. All blends need to be stirred prior to application.

The pot life of TEGO® RC 1400 series silicones with TEGO® PC 1467 added is minimum 72 hours if stored properly (avoid exposure to sunlight and heat). Maximum bath life can be longer but is very dependant on local storage conditions, especially temperature.

Suitability tests

Before using any new silicone formulation, we recommend checking that the final product meets the target requirements.

This includes but is not limited to:

- Compatibility of release coating against targeted adhesives using ageing tests at both low and high temperatures.
- The influence of electron beam or Gamma irradiation on aging and release, e.g. sterilization.
- The influence of secondary UV exposure on release and aging, e.g. when curing UV printing inks on label stock with a clear face stock.

Thermal ageing or post-irradiation may cause a property change in the final product.

Storage stability

TEGO® RC 1401 should be stored in the dark at temperatures below 30 °C (86 °F). Keep oxidizing, acidic or alkaline substances away from TEGO® RC Silicones. The guaranteed shelf life is 24 months, when stored under these conditions and in original sealed containers.

Packaging

25 kg (55 lbs.) plastic containers
pallet size: 12 x 25 kg = 300 kg

200 kg (440 lbs.) plastic lined steel drums
pallet size: 4 x 200 kg = 800 kg

1 000 kg (2 200 lbs.) container

Hazardous goods classification

Information concerning

- classification and labelling according to regulations for transport and for dangerous substances
- protective measures for storage and handling
- measures in case of accidents and fire
- toxicity and ecological effects

is given in our material safety data sheets.

01/2019

Trademark notice and legal notice

This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

(Status: July 2015)

Evonik Nutrition & Care GmbH

Goldschmidtstr. 100, 45127 Essen, Germany

Phone Europe +49 201 173-2665, Asia +86 21 61191 125, Americas +1 804 727 0700

interface-performance@evonik.com, www.evonik.com/interface-performance